

WHAT IS CLAIMED IS:

1. A fire retarding polypropylene composition comprising:
 - (a) a copolymer of polypropylene resin in which ethylene/propylene rubber has been grafted onto the polypropylene chains; and
 - (b) at least about 50% but not greater than 60% by weight of a magnesium hydroxide coated with an anionic surface active agent, the magnesium hydroxide having:
 - (i) a strain in the $\langle 101 \rangle$ direction of not more than 3.0×10^{-3} ,
 - (ii) a crystallite size in the $\langle 101 \rangle$ direction of more than 800 \AA , and
 - (iii) a specific surface area, determined by the BET method, of less than $20 \text{ mg}^2/\text{g}$,wherein the composition being adapted to meet FMRC standards for use in a clean room.
2. The composition of claim 1 wherein said copolymer contains between about 80% and about 85% polypropylene and between about 15% and about 20% ethylene/propylene rubber.
3. The composition of claim 1 wherein the melt flow index of said copolymer is less than about 1 gram per 10 minute interval.
4. The composition of claim 1 wherein said copolymer is halogen-free.